



PCT/GB 2004 / 0 0 2 7 9 2



INVESTOR IN PEOPLE

BEST AVAILABLE COPY

**PRIORITY
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ


REC'D 21 JUL 2004
WIPO PC

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

Dated 15 July 2004



02JUL03 E819411-1 002847
P01/7700 0.00-0315409.3

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

THE PATENT OFFICE

H

1 JUL 2003

NEWPORT

The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

1. Your reference

HL85630/000/DLB

2. Patent application number

(The Patent Office will fill in this part)

0315409.3

3. Full name, address and postcode of the or of each applicant (underline all surnames)

Imerys Minerals Limited
Par Moor Centre
Par Moor Road
Par, Cornwall PL25 2SQ
United Kingdom

04858293003

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

United Kingdom

4. Title of the invention

PARTICULATE CLAY MATERIALS AND POLYMER COMPOSITIONS INCORPORATING THE SAME

5. Name of your agent (if you have one)

Haseltine Lake

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Imperial House
15-19 Kingsway
London
WC2B 6UD

Patents ADP number (if you know it)

34001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Yes

Patents Form 1/77

Enter the number of sheets for any of the following items you are filing with this form.
~~Do not count copies of the same document~~

Continuation sheets of this form

Description 22 ✓

Claim(s) 4 ✓

Abstract 1 ✓

Drawing(s) 0

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

11.

I/We request the grant of a patent on the basis of this application.

Signature

Haseltine Lake

Date

01-July-2003

12. Name and daytime telephone number of person to contact in the United Kingdom

Mr David L. Brown

[0117] 910 3200

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

PARTICULATE CLAY MATERIALS AND POLYMER
COMPOSITIONS INCORPORATING THE SAME

Field of the Invention

5

The present invention relates to particulate clay materials and more especially to particulate clay materials suitable for use as fillers in polymer compositions. The invention also relates to novel polymer compositions incorporating the particulate clay materials, to process intermediates from which
10 such compositions may be formed and to articles made from the compositions.

Background of the Invention

Flame retardant polymer compositions are widely used, particularly in
15 locations where there is a risk of high temperatures and/or fire, or where the consequences of burning of the polymer composition would be catastrophic. For example, the sheathing or coating of electrical cables must meet legally specified flame retardancy standards, to limit the risk of failure of electrical systems in the event of a fire and to limit the risk of a fire being started or spread
20 as a result of overheating of the cable by the electric current. The cable sheathing or coating will be rated to withstand a specified temperature.

Generally speaking, flame retardant polymer compositions include additives which can have one or more of the following effects on exposure of the composition to fire: (i) char promotion, in which the combusted composition
25 forms a solid mass ("char"), which provides an insulating layer against the fire heat, inhibiting escape of volatile combustible materials from the composition and inhibiting inward diffusion of oxygen; (ii) imparting drip resistance, in which the tendency of a thermoplastic polymer to drip when heated is reduced; (iii) promotion of heat absorption, in which the additive removes heat from the
30 system; and (iv) promotion of heat quenching, in which the additive inhibits combustion in the gas phase by interfering with the chemical reactions which spread and maintain a flame.

Known char forming additives include phosphorus-containing compounds, boron-containing compounds and metal salts such as alkali metal salts of sulphur-containing compounds, which can fuse and solidify at flame temperatures, thereby creating a ceramic-like or glass-like mass which structurally supports the char.

Known drip suppressing additives for thermoplastic polymers include polytetrafluoroethylene (PTFE). The PTFE is typically present at an amount of up to about 5% by weight of the total composition, and forms fibrils which stabilise the thermoplastic polymer under molten conditions. See, for example, WO-A-99/43747 and the prior publications referred to therein and in the search report thereon, the contents of which are incorporated herein by reference.

Known heat absorbing additives include metal hydroxides or hydrates such as alumina trihydrate (ATH ; $\text{Al}(\text{OH})_3$) or magnesium hydroxide ($\text{Mg}(\text{OH})_2$). These additives are believed to work by absorbing heat to evaporate water contained in their structure.

Known heat quenching (flaming resistance) additives include free radical scavengers such as organic halogen-containing compounds such as brominated and chlorinated hydrocarbons. These additives are believed to work by releasing halogens into the flame, which inhibit combustion of the gas phase. Synergistic co-additives such as antimony oxide may be present, to enhance the heat quenching effects of the free radical scavengers. See, for example, US Patent No. 4582866 and the prior publications referred to therein and in the search report thereon, the contents of which are incorporated herein by reference.

The known additives are not entirely satisfactory, however, and the need for alternative and improved additives remains. For example, additives such as PTFE can adversely affect the surface finish of the composition. The use of halogen-containing compounds is believed to cause health problems and environmental damage. The additives can also adversely affect impact strength and impact resistance of the composition, or other physical properties. At the same time, cost pressures can urge that the level of additive used is as low as possible.

Proposals have been made to include certain clays as flame retardant additives in polymer compositions, in an attempt to answer some of these difficulties. US Patent No. 5946309, the disclosure of which is incorporated herein by reference, describes generally a coarse particle size kaolin clay product having an average equivalent particle diameter of about 4.5 to 6.0 microns (μm) as measured using a Micromeritics Sedigraph 5100 unit, and a BET surface area of about 8 to 11 m^2/g , and its use as a filler for flame retardant and other polymeric compositions.

US Patent No. 4960816, the disclosure of which is incorporated herein by reference, describes certain particulate kaolin clay products in which the surfaces of the kaolin particles have certain amide polymers associated therewith, and suggests the use of such materials as fillers for polymeric compositions.

The present invention is based on the surprising finding that, by using in a polymer composition a novel particulate clay filler which is surface-modified by treatment with at least one organic compound having an organic portion and a basic portion, a useful degree of flame resistance can be obtained in conjunction with generally desirable physical properties of the polymer composition.

Brief Description of the Invention

According to the present invention in a first aspect, there is provided a particulate clay material in which the clay particles are surface-modified by treatment with at least one organic compound comprising an organic portion and a basic portion.

The term "surface-modified" used herein is to be understood broadly, and is not limited, for example, to uniform coatings or to coatings which cover the entire surface area of a particle. Particles in which discrete regions of the surface are modified with the organic compound, and in which areas of the surface are associated with discrete molecules of the organic compound, will be understood as being surface-modified within the terms of the present invention.

The organic compound may suitably be present in an amount of between about 0.1 and about 5 wt% based on the dry weight of the particulate clay material, more preferably between about 0.5 and about 2 wt%, e.g. about 1 wt%.

The organic compound may be polymeric or non-polymeric. The
5 organic compound may optionally include at least one functional group associated with the organic portion, more particularly at least one functional group which can interact with a polymer or other material to be filled using the particulate clay material of the present invention.

Without wishing to be bound by theory, it is believed that the basic
10 portion of the organic compound serves in use to anchor the compound directly to the surface of a clay particle by direct acid/base interaction with an acidic site on the clay particle, including, for example, aluminium atoms with broken bonds. It is therefore preferred that the organic compound will have sufficient basic character to provide an effective acid/base interaction with acidic
15 aluminium sites on the surface of the particle.

It is preferred that the particulate clay material is in the form of substantially dry particles. These substantially dry particles are preferably present in the substantial absence of particles of the organic compound(s). The population of particles may consist essentially of the surface-modified clay
20 according to the first aspect of the present invention, or may be in admixture with other desired particulate ingredients, as described in more detail below. Such forms are particularly suitable for addition to an organic material to be filled.

The particulate clay material will preferably have a mean equivalent
25 particle diameter less than or equal to about 4 microns (μm), and a particle shape factor which is greater than about 10, and preferably up to about 150.

According to the present invention in a second aspect, there is provided a method of preparing a particulate clay material according to the first aspect of the invention, comprising contacting a particulate clay material which is not
30 surface-modified with the organic compound or compounds with a sufficient quantity of the organic compound or compounds under conditions whereby the

said organic compound or compounds associate with the clay particles to surface-modify the same.

According to the present invention in a third aspect, there is provided a polymer composition comprising a polymer and a particulate clay filler distributed in the polymer composition, wherein the particulate clay filler is a particulate clay material according to the first aspect of the invention. The polymer composition is suitably a flame retardant polymer composition.

The polymer composition may suitably include one or more further components, which may be selected from one or more conventional flame retardant component, one or more conventional non-flame retardant component, or both. Any such further components will suitably be present in a smaller weight proportion than the essential components of the composition. The essential components of the composition preferably constitute the majority (i.e. over half) of the weight of the composition.

The conventional flame retardant component, when present, may, for example, be selected from phosphorus-containing compounds, boron-containing compounds, metal salts, metal hydroxides, metal oxides, hydrates thereof, organoclays (including ion-exchanged and any other modified organoclays), halogenated hydrocarbons, and any combination thereof, typically boric acid, a metal borate and any combination thereof. A preferred flame retardant component is ATH.

The conventional non-flame retardant component, when present, may, for example, be selected from pigments, colorants, anti-degradants, anti-oxidants, impact modifiers, inert fillers, slip agents, antistatic agents, mineral oils, stabilisers, flow enhancers, mould release agents, nucleating agents, clarifying agents and any combination thereof.

According to the present invention in a fourth aspect, there is provided a particulate filler for a flame retardant polymer composition, the filler comprising a mixture of a particulate clay and one or more further particulate flame retardant (for example, ATH), wherein the particulate clay is a surface-modified particulate clay material according to the first aspect of the invention.

For processing to form the polymer composition, the components will preferably be mixed, the polymer component being present as liquid or particulate solid, optionally as one or more precursors of the polymer component. Where one or more precursors of the polymer component are used,
5 the mixture will typically then be cured, optionally after further conventional processing steps, to provide the polymer composition. Such a process and the resultant mixture constitute respectively fifth and sixth aspects of the present invention.

According to the present invention in a seventh aspect, there is provided
10 an article, for example an electrical product or other article comprising a sheath, coating or housing, formed from a flame retardant polymer composition according to the second aspect of the present invention.

Detailed Description of the Invention

15

Particulate Clay

The particulate clay may comprise hydrous kaolin, partially calcined kaolin (metakaolin), fully calcined kaolin, ball clay, talc, mica or any
20 combination thereof. The kaolin clay is preferably a hydrous kaolin. Mixtures of different clays may be used, provided that the particulate clay has the required mean equivalent particle diameter and the required shape factor.

A kaolin product of high shape factor is considered to be more "platey" than a kaolin product of low shape factor. "Shape factor" as used herein is a
25 measure of an average value (on a weight average basis) of the ratio of mean particle diameter to particle thickness for a population of particles of varying size and shape as measured using the electrical conductivity method and apparatus described in GB-A-2240398/US-A-5128606/EP-A-0528078 and using the equations derived in these patent specifications. "Mean particle diameter" is
30 defined as the diameter of a circle which has the same area as the largest face of the particle. In the measurement method described in EP-A-0528078 the electrical conductivity of a fully dispersed aqueous suspension of the particles

under test is caused to flow through an elongated tube. Measurements of the electrical conductivity are taken between (a) a pair of electrodes separated from one another along the longitudinal axis of the tube, and (b) a pair of electrodes separated from one another across the transverse width of the tube, and using the
5 difference between the two conductivity measurements the shape factor of the particulate material under test is determined.

Incidentally, the "aspect ratio" parameter of the kaolin clay product of the prior art US Patent No. 5946309 is not numerically the same as the "shape factor" parameter of the kaolin used in the present invention. For example, for
10 one clay which we have tested, it is found experimentally that an "aspect ratio" of 9 according to the prior art determination corresponds to a "shape factor" according to the present invention of about 65 ± 5 .

The mean (average) equivalent particle diameter (d_{50} value) and other particle size properties referred to herein for the particulate clay are as measured
15 in a well known manner by sedimentation of the particulate material in a fully dispersed condition in an aqueous medium using a Sedigraph 5100 machine as supplied by Micromeritics Instruments Corporation, Norcross, Georgia, USA (telephone: +1 770 662 3620; web-site: www.micromeritics.com), referred to herein as a "Micromeritics Sedigraph 5100 unit". Such a machine provides
20 measurements and a plot of the cumulative percentage by weight of particles having a size, referred to in the art as the 'equivalent spherical diameter' (esd), less than given esd values. The mean particle size d_{50} is the value determined in this way of the particle esd at which there are 50% by weight of the particles which have an equivalent spherical diameter less than that d_{50} value.

25 The particulate clay of the present invention will preferably have a mean equivalent particle diameter (d_{50}) less than or equal to about 4 microns (μm) (by Sedigraph), e.g. less than $4.5\mu\text{m}$, particularly less than $4.0\mu\text{m}$, e.g. less than about $3\mu\text{m}$, and a particle shape factor which is greater than about 10, e.g. greater than about 20, and preferably up to about 150.

30 The value of d_{50} may, for example, be in the range of about $0.1\mu\text{m}$ to about $3\mu\text{m}$, for example about $0.1\mu\text{m}$ to about $2\mu\text{m}$.

In the case of particulate clays present in the polymer composition at a relatively high number of particles per unit volume, the value of d_{50} will generally be relatively low, to provide the required particle number. In embodiments of the polymer composition of the present invention, for example, the particle number per unit volume is at least about 2 particles per $100\ \mu\text{m}^3$, for example at least about 5 particles per $100\ \mu\text{m}^3$ or at least about 10 particles per $100\ \mu\text{m}^3$. Normally, in compositions of this aspect of the invention, the particle number per unit volume in the polymer composition will be no greater than about 10,000 particles per $100\ \mu\text{m}^3$.

The clay filler is suitably present in the polymer composition according to the present invention at amounts in the general loading range between about 10 and about 250 parts by weight per hundred of polymer, and more preferably between about 50 and about 200 parts per hundred, for example about 160 parts by weight per hundred of polymer.

Organic Compound

The organic portion of the compound may suitably comprise (or more preferably may consist essentially of) a straight or branched chain alkyl group having at least 8 carbon atoms, for example between 8 and 24 carbon atoms, such as, for example, a C_{13} , C_{14} , C_{15} , C_{16} , C_{17} , C_{18} , C_{19} , C_{20} , C_{21} , C_{22} or C_{23} alkyl group. Alternatively, the organic portion may comprise (or more preferably consist essentially of) one or more cyclic organic groups, which may be saturated, unsaturated or aromatic, and may optionally include one or more heteroatoms, for example selected from O, N and S. The cyclic organic group may, for example, include at least one six-membered ring. The organic portion of the compound may include one or more substituent groups, such as, for example, functional groups which can favourably interact with a polymeric or other material to be filled using the surface-modified clay particles. The interaction may, for example, involve covalent bonding, cross-linking, hydrogen bonding, chain entanglement or ionic interaction. Suitable functional substituent groups include, for example, polar or non-polar groups, and hydrophobic or

hydrophilic groups. Examples of such groups include amide or polyamide groups (which can favourably interact with polyamides such as nylon), carboxyl groups, vinyl groups (which can favourably interact with natural or synthetic rubbers), mercapto or other sulphur-containing groups (which can favourably
5 interact with natural or synthetic rubbers), or alkylamino groups such as ethylamino or propylamino groups.

The basic portion of the compound comprises any group which is capable of associating with the acid sites of the clay particles. The basic portion may, for example, include at least one primary, secondary or tertiary amine
10 group. The basic portion of the organic compound preferably comprises one or more primary amine group NH_2 .

The organic compound may be monomeric or polymeric. The term "polymeric" includes homopolymers and copolymers.

The organic compound may, for example, be selected from alkyl mono-
15 amines containing between 8 and 24 carbon atoms in a straight or branched alkyl portion (e.g. hydrogenated-tallowalkyl-amine), organic polyamines, and cyclic mono- or poly-amines including at least one cyclic ring system having at least 6 atoms comprising the ring (e.g. melamine). These compounds may optionally carry further functional substituents on the organic portion, as
20 described above.

The surface-modified particulate clay material of the present invention is preferably obtained by contacting a particulate clay having the desired particle size distribution and shape factor with the organic compound under conditions whereby the compound will associate with the surface of the clay particles. The
25 particulate starting material may be uncoated (not surface-modified) or may be surface-modified with one or more different compounds which do not prevent the desired degree of association between the organic compound and the particles in accordance with the present invention. The organic compound may suitably be intimately admixed with the particles of the clay to obtain optimum
30 contact between the materials. The organic compound may be used in the form of solid particles (e.g. prills) or may be entrained in a suitable solvent for the

coating process. The coating process may suitably be carried out at an elevated temperature.

The particulate clay material for use in the method of preparing the surface-modified material according to the invention may be prepared by light
5 comminution, e.g. grinding or milling, of a coarse clay (e.g. a coarse kaolin) to give suitable delamination thereof. The comminution may be carried out by use of beads or granules of a plastics, e.g. nylon, grinding or milling aid. The coarse clay may be refined to remove impurities and improve physical properties using well known procedures. The clay mineral may be treated by a known particle
10 size classification procedure, e.g. screening and/or centrifuging, to obtain particles having a desired d_{50} value.

A range of particulate clay materials are available, which have the required particle size and shape factor, or can easily be processed in ways well known to the skilled worker to arrive at the required particle size and shape
15 factor.

Polymer

The polymer to be filled in accordance with the present invention
20 comprises any natural or synthetic polymer or mixture thereof. The polymer may, for example, be thermoplastic or thermoset. The term "polymer" used herein includes homopolymers and copolymers, as well as crosslinked and/or entangled polymers and elastomers such as natural or synthetic rubbers and mixtures thereof. Specific examples of suitable polymers include, but are not
25 limited to, polyolefins of any density such as polyethylene and polypropylene, polycarbonate, polystyrene, polyester, acrylonitrile-butadiene-styrene copolymer, nylons, polyurethane, ethylene-vinylacetate polymers, and any mixture thereof, whether cross-linked or un-cross-linked.

The term "precursor" as applied to the polymer component will be
30 readily understood by one of ordinary skill in the art. For example, suitable precursors may include one or more of: monomers, cross-linking agents, curing systems comprising cross-linking agents and promoters, or any combination

thereof. Where according to the invention the particulate clay material is mixed with precursors of the polymer, the polymer composition will subsequently be formed by curing and/or polymerising the precursor components to form the desired polymer.

5 The particulate clay material may suitably be present in the polymer composition at a particle number per unit volume of at least about 1 particle per $100 \mu\text{m}^3$.

10 The parameter of particle number per unit volume (referred to herein as $N_{\text{per unit volume}}$ or N_{puv}) of the particulate clay filler when present in the filled polymer composition is calculated from the d_{50} of the clay by Sedigraph (d) and the volume fraction of the clay in the polymer composition (ϕ), according to the following relationship:

$$N_{\text{puv}} = \frac{6}{\pi} \frac{\phi}{d^3}$$

15

Here, d , measured by the Sedigraph is related to both the average diameter of the clay (mineral) disk or platelet (D) and the shape factor NSF as follows:

$$d = D \sqrt{\frac{3}{2} \frac{\arctan NSF}{NSF}}$$

20

(see Jennings et al, Particle size measurement: the equivalent spherical diameter, Proc. R. Soc. Lond., A419, 137-149, 1988).

Flame Retarding Component

25

As stated above, the polymer composition according to the present invention may suitably contain one or more further flame retarding components. Such components may, for example, be selected from one or more of the following:

30

- (i) One or more char promoter;
- (ii) One or more drip suppressant;
- (iii) One or more heat absorber; and
- (iv) One or more heat quencher (ignition suppressant).

5

Any conventional such components may be used, as will be apparent to one of ordinary skill in this art. Examples of such components include:

Char promoters and drip suppressants

10

Phosphorus-containing compounds (e.g. organophosphates or phosphorus pentoxide), boron-containing compounds (e.g. boric acid and metal borates such as sodium borate, lithium metaborate, sodium tetraborate or zinc borate), organoclays (e.g. smectite clays such as bentonite, montmorillonite, hectorite, saponite and ion-exchanged forms thereof, suitably ion-exchanged forms incorporating cations selected from quaternary ammonium and alkylimidazolium ions), metal oxides (e.g. lead dioxide);

15

Heat absorbers

20

Metal salts, metal hydroxides (e.g. ATH, magnesium hydroxide), hydrates thereof (e.g. sodium tetraborate decahydrate);

Heat quenchers

25

Halogenated hydrocarbons (e.g. halogenated carbonate oligomers, halogenated phenyl oxides, halogenated alkylene-bis-phthalidimides and halogenated diglycyl ethers), optionally together with metal oxides (e.g. antimony oxide).

30

The further flame retarding component, when present, is suitably present in the polymer composition or the filler material according to the present invention at amounts between about 5 and about 70% by total weight of the

flame retarding filler components, and more preferably between about 5 and about 50% by weight.

Non-Flame Retarding Component

5

The polymer composition may include one or more non-flame retardant additives for polymers, for example selected from pigments, colorants, anti-degradants, anti-oxidants, impact modifiers (e.g. core-shell graft copolymers), unmodified or conventional fillers (e.g. talc, mica, wollastonite, glass or a mixture thereof), slip agents (e.g. erucamide, oleamide, linoleamide or steramide), coupling agents (e.g. silane coupling agents), peroxides, antistatic agents, mineral oils, stabilisers, flow enhancers, mould release agents (e.g. metal stearates such as calcium stearate and magnesium stearate), nucleating agents, clarifying agents, and any combination thereof.

15

The non-flame retarding component, when present, is suitably present in the polymer composition or the particulate clay material according to the present invention at amounts up to about 50% by total weight of the flame retarding component, and more preferably between up to about 30% by weight.

20

The coupling agent, where present, serves to assist binding of the filler particles to the polymer. Suitable coupling agents will be readily apparent to those skilled in the art. Examples includes silane compounds such as, for example, tri-(2-methoxyethoxy) vinyl silane. The coupling agent is typically present in an amount of about 0.1 to about 2% by weight, preferably about 1% by weight, based on the weight of the total particulate filler.

25

Preparation of the Compositions

Preparation of the polymer compositions of the present invention can be accomplished by any suitable mixing method known in the art, as will be readily apparent to one of ordinary skill in the art.

30

Such methods include dry blending of the individual components or precursors thereof and subsequent processing in conventional manner. Certain

of the ingredients can, if desired, be pre-mixed before addition to the compounding mixture. For example, if desired the coupling agent can be pre-mixed with the surface-modified particulate clay filler according to the present invention, before addition of the clay to the mixture.

5 In the case of thermoplastic polymer compositions, such processing may comprise melt mixing, either directly in an extruder for making an article from the composition, or pre-mixing in a separate mixing apparatus such as a Banbury mixer. Dry blends of the individual components can alternatively be directly injection moulded without pre-melt mixing.

10 The filler material according to the fourth aspect of the present invention can be prepared by mixing of the components thereof intimately together. The said filler material is then suitably dry blended with the polymer and any desired additional components, before processing as described above.

 For the preparation of cross-linked or cured polymer compositions, the
15 blend of uncured components or their precursors, and, if desired, the clay and any desired non-clay component(s), will be contacted under suitable conditions of heat, pressure and/or light with an effective amount of any suitable cross-linking agent or curing system, according to the nature and amount of the polymer used, in order to cross-link and/or cure the polymer.

20 For the preparation of polymer compositions where the clay filler and any desired other component(s) are present *in situ* at the time of polymerisation, the blend of monomer(s) and any desired other polymer precursors, clay and any other component(s) will be contacted under suitable conditions of heat, pressure and/or light, according to the nature and amount of the monomer(s) used, in
25 order to polymerise the monomer(s) with the clay and any other component(s) *in situ*.

Articles

30 The polymer compositions can be processed to form, or to be incorporated in, articles of commerce in any suitable way. Such processing may include compression moulding, injection moulding, gas-assisted injection

moulding, calendaring, vacuum forming, thermoforming, extrusion, blow moulding, drawing, spinning, film forming, laminating or any combination thereof. Any suitable apparatus may be used, as will be apparent to one of ordinary skill in this art.

5 The articles which may be formed from the compositions are many and various. Examples include sheaths for electrical cables, electrical cables coated or sheathed with the polymer composition, and housings and plastics components for electrical appliances (e.g. computers, monitors, printers, photocopiers, keyboards, pagers, telephones, mobile phones, hand-held
10 computers, network interfaces, plenums and televisions).

Examples

Embodiments of the present invention will now be described, purely by
15 way of example and without limitation, with reference to the following Examples.

Preparation of Test Materials

20 The following Examples illustrate the preparation of the test materials embodying the present invention and the comparison materials incorporating unmodified clay filler materials and ATH alone.

Batches of the composition were prepared using a conventional 1.57 litre Banbury mixer, fill factor about 65%, according to the following standard
25 composition (for 61% filler loading). The range of actual filler loadings prepared is shown in Table 2 below.

	Polymer	100phr
	Filler	160phr
30	Antioxidant	1phr
	Graft Promoter	0.03phr
	Coupling Agent	1.6phr

The ingredient materials were as follows:

Polymer

- 5 The polymer used was Escorene UL00119, an ethylene-vinylacetate copolymer (19 wt-% vinyl acetate), available from Exxon-Mobil Corporation.

Filler

- 10 The filler used in each case was a 50:50 by weight mixture of powdered fine precipitated grade ATH (Superfine SF7, available from Alcan Chemicals) and the particulate kaolin clay.

- The unmodified clays used were designated B, G, H, J and O. These unmodified clays were used in preparing comparison compositions in which the
15 filler was a 50:50 by weight mixture of ATH and unmodified clay. The chemical analysis data (by X-ray fluorescence) for these clays are set out in Table 1a below, with the exception of clays H and O, for which this data is not available (NA = not available). Table 1b shows data relating to the mean equivalent particle diameter and shape factor, as well as corresponding data
20 relating to the ATH co-filler used in the polymer compositions. The clays were particulate hydrous kaolin clays which are all available commercially, or can readily be prepared from commercially available materials.

Table 1a

25

<i>Clay</i>	XRF chemical analysis						K ₂ O	Na ₂ O	Loss on Ignition
	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	CaO	MgO			
<i>B</i>	49.4	35.58	0.95	0.08	0.05	0.25	2.43	0.09	11.17
<i>G</i>	48.35	36.7	0.69	0.03	0.04	0.21	1.18	0.09	12.79
<i>H</i>					NA				
<i>J</i>	55.97	29.17	1.24	0.98	0.18	0.42	2.76	0.04	8.88
<i>O</i>					NA				

Table 1b

<i>Filler Component</i>	NSF	d50 (μm)	Sedigraph % below						
			10	5	2	1	0.75	0.5	0.25
<i>Superfine SF7 ATH</i>	3	0.8	95.1	96	90.2	70.4	43.7	11.1	<5%
<i>Clay B</i>	70	1.61	93.9	83.7	52.6	34.2	27.7	18.7	10.2
<i>Clay G</i>	25	0.41	99.4	98.9	92.6	80.3	72.1	56.8	30.4
<i>Clay H</i>	35	0.2	97.9	96.9	92.1	86	82.5	76.4	52.9
<i>Clay J</i>	25	0.12	>99	99	97.8	97.6	97.8	96.8	81.5
<i>Clay O</i>	18	0.41	100	98.8	91	76.6	69.4	57.5	30.8

5 A further comparison composition was also prepared, filled with ATH in the absence of a clay co-filler.

Batches of surface-modified clays were prepared by treating each of clays B, G, H, J and O with 1 wt.-% Armeen HT (hydrogenated tallow-alkyl-amine), available from Akzo-Nobel. The treatment was carried out by mixing the clay and the amine prills in a high speed mixer for 10 minutes at a temperature of 70°C. The coated versions of clays B, G, H, J and O are referred to herein as clays B*, G*, H*, J* and O* respectively.

In addition, corresponding compositions were prepared using clays O and O*, but omitting the silane coupling agent. These compositions were tested in the DSC test and the resulting data is included in Table 5 below.

Antioxidant

The antioxidant used was Irganox 1010, a commercially available phenolic antioxidant available from Ciba.

Graft Promoter

The graft promoter used was Perkadox BC40-40MB-gr (dicumyl peroxide), which serves to promote grafting of the unsaturated silane coupling agent to the polymer without inducing too much matrix cross-linking.

Coupling Agent

The coupling agent used was the silane tri-(2-methoxyethoxy) vinyl silane, available from Kettlitz.

5

Preparation of Test Samples

Each test composition was made into a sheet using twin roll mill set up at 120°C.

10

Plaques were then pressed at 160°C according to the following sequence: the plaques were pressed together with very little pressure for 1 minute; a 20 bar pressure was applied for 1 minute; then a 50 bar pressure for a further 1 minute; and then the pressure was increased to about 200 bar for a further 3 minutes.

Plaques of 1.8 mm thick were produced for mechanical testing and the UL-64 vertical burning test. Plaques of 3 mm thickness were produced for the Limiting Oxygen Index (LOI) test and the assessment of char strength. The dimensions of the test samples as cut from the plaques are given below in the discussion of each test.

20

Test Methods

Mechanical Properties

The mechanical properties tensile strength (at peak) and elongation at break of were tested for each composition using a Monsanto tensometer. Test pieces were conditioned for 48 hours at 23°C, 50% relative humidity (RH) prior to testing. The test speed was set up at 100 mm/min.

30

Underwriters Laboratories Standard UL94 Flammability Test (ASTM 3801)

The UL94 vertical burning test was carried out by clamping, igniting and studying the rate of burning of conditioned samples. Thin samples of 125 x 12.5

x 1.8 mm were used for the test in order to show differences in the burning behaviour (compounds could not be compared at 3 mm thickness since they all achieved V0 rating, i.e. burning less than 10 seconds and no dripping).

The test piece was clamped vertically by its top 6 mm, and positioned
5 300 mm above a small piece of cotton wool stretched to 50 x 50 mm. The test piece was then lit at its bottom using a Bunsen burner with a blue flame of 20 mm length, held 10 mm away from the base of the sample for 10 seconds. If the flame went out, the burner was applied for a further 10 seconds and the time it took to extinguish itself was again recorded. Otherwise, the time it took for the
10 sample to burn all the way up to the clamp was recorded.

Oxygen Index

A Ceast Oxygen Index apparatus was used to determine the minimum
15 oxygen concentration necessary to keep a sample burning for 3 minutes. The samples were cut out as 70 x 6.5 x 3 mm pieces and were conditioned for 48 hours at 23°C and 50% RH, according to British Standard BS2782, method 141D.

20 Thermal Stability

A modified procedure based on an ASTM D 3895-98 was used to study the thermal stability / oxidation of the compounds. The oxidation induction time (OIT) was measured using a Perkin-Elmer DSC-7 Differential Scanning
25 Calorimeter (DSC). The following DSC sequence was applied:

1. Heat from 20°C to 225°C at 20°C per minute
2. Hold at 225°C for 5 minutes
3. Hold at 225°C until polymer degrades

30

Steps 1 and 2 were conducted in a nitrogen environment at a pressure of ca. 25 psi. Step 3 was conducted in an oxygen environment at 40 psi.

Results

The **tensile elongation** data for the tested samples are shown in Table 2 below. For convenience, the results for the samples containing unmodified filler (comparisons) are shown in the left hand of the two elongation data columns; the results for the samples containing coated filler (invention) are shown in the right hand column.

Table 2

<i>Clay Filler Component (present with ATH)</i>	Filler Loading (wt.%)	Elongation (%)	Elongation (%)
<i>G</i>	53.7	224	
<i>G</i>	52.1	147	
<i>G</i>	52.1	147	
<i>H</i>	59.1	171	
<i>J</i>	48.6	434	
<i>J</i>	51.7	187	
<i>O</i>	50.3	257	
<i>O</i>	52.9	157	
<i>O</i>	52.9	157	
<i>O</i>	61.3	105	
<i>O</i>	61.3	98	
<i>O</i>	61.9	95	
<i>B</i>	55.5	141	
<i>B</i>	60	117	
<i>B</i>	61.9	82	
<i>G*</i>	49		562
<i>G*</i>	51.5		242
<i>H*</i>	61.5		162
<i>J*</i>	49.8		421
<i>O*</i>	48.5		589
<i>O*</i>	51.2		343
<i>O*</i>	60.6		135
<i>B*</i>	60.9		137
<i>B*</i>	58.5		166

The **fire retardancy** data (average of three different clays) are shown in Table 3 below:

Table 3

	Uncoated	Coated
<i>Burning characteristics UL94</i>	1 burn	2 burns (re-ignition needed)
<i>Total typical burning time/s</i>	112	190

5

The Limiting Oxygen Index data are shown in Table 4 below:

Table 4

10

<i>Filler Component (clays are present with ATH)</i>	Filler loading (wt.%)	LOI (%)
<i>ATH alone</i>	60.9	39
<i>Clay O</i>	61.3	30.5
<i>Clay O*</i>	60.6	31
<i>Clay H</i>	59.1	29
<i>Clay H*</i>	61.5	31.5
<i>Clay B</i>	55.6	26.5
<i>Clay B*</i>	58.1	29.5

15 The DSC data shown in Table 5 below indicate that degradation of the polymer can be delayed when the filler incorporates an amine-modified clay.

Table 5

<i>Filler Component (clays are present with ATH)</i>	Filler loading (wt.%)	OIT (min)
<i>Clay O</i>	61.3	16.7
<i>Clay O*</i>	60.6	17.1
<i>Clay H</i>	59.1	15.2
<i>Clay H*</i>	61.5	28.8
<i>Clay O – no silane</i>	61.8	8.3
<i>Clay O* - no silane</i>	61.2	19.7

20

Discussion

The use of a clay filler surface-modified with an organic coating compound in accordance with the present invention improves the flame resistance, oxygen
5 index and mechanical properties of a thermoplastic resin, in comparison with a resin filled with the corresponding unmodified clay filler.

The foregoing broadly describes the present invention, without limitation. Variations and modifications as will be readily apparent to those of ordinary
10 skill in this art are intended to be included within the scope of this application and subsequent patent(s).

CLAIMS

1. A particulate clay material which is surface-modified with at least one organic compound comprising an organic portion and a basic portion.
- 5 2. A particulate clay material according to claim 1, wherein the organic portion of the organic compound comprises a straight or branched chain alkyl group having between 8 and 24 carbon atoms.
- 10 3. A particulate clay material according to claim 1, wherein the organic portion of the organic compound comprises one or more cyclic organic groups,
----- which may be saturated, unsaturated or aromatic, and may optionally include one or more heteroatoms.
- 15 4. A particulate clay material according to any one of the preceding claims, wherein the organic portion of the organic compound includes one or more functional substituent groups which can favourably interact with a polymer filled using the material.
- 20 5. A particulate clay material according to any one of the preceding claims, whereing the basic portion of the organic compound comprises one or more primary amine group NH_2 .
- 25 6. A particulate clay material according to claim 1, wherein the organic compound is selected from hydrogenated-tallowalkyl-amine, organic mono-amines, organic polyamines, melamine, and derivatives thereof in which the organic portion carries at least one functional substituent group which can favourably interact with a polymer filled using the material.
- 30 7. A particulate clay material according to any one of the preceding claims, in the form of substantially dry particles.

-
8. A particulate clay material according to any one of the preceding claims, having a mean equivalent particle diameter less than or equal to about 4 microns (μm), and a particle shape factor which is greater than about 10.
- 5 9. A particulate clay material according to any one of the preceding claims, wherein the clay is selected from hydrous kaolin, partially calcined kaolin (metakaolin), fully calcined kaolin, ball clay, talc, mica and any combination thereof.
- 10 10. A method of preparing a particulate clay material according to any one of the preceding claims, comprising contacting a particulate clay which is not
surface-modified with the organic compound or compounds with a sufficient
quantity of the organic compound or compounds under conditions whereby the
said organic compound or compounds associate with the particles of the
15 particulate clay to surface-modify the same.
11. A polymer composition comprising a polymer and a particulate clay filler distributed in the polymer composition, wherein the particulate clay filler is a material according to any one of claims 1 to 9.
- 20 12. A polymer composition according to claim 11, wherein the polymer is a thermoplastic polymer.
13. A polymer composition according to claim 11 or claim 12, which is a
25 flame retardant polymer composition.
14. A polymer composition according to any one of claims 11 to 13, wherein the particulate clay filler is present in the polymer composition at a particle number per unit volume of at least about 1 particle per $100 \mu\text{m}^3$.
- 30 15. A polymer composition according to claim any one of claims 11 to 14, comprising one or more further components selected from one or more

conventional flame retardant component, one or more conventional non-flame retardant component, and both.

16. A polymer composition according to claim 15, wherein the conventional
5 flame retardant component is selected from phosphorus-containing compounds, boron-containing compounds, metal salts, metal hydroxides, metal oxides, hydrates thereof, organoclays, halogenated hydrocarbons, and any combination thereof.

10 17. A polymer composition according to claim 15, wherein the conventional flame retardant component comprises ATH.

18. A polymer composition according to any one of claims 15 to 17, wherein
15 the conventional non-flame retardant component is selected from pigments, colorants, anti-degradants, anti-oxidants, impact modifiers, inert fillers, slip agents, antistatic agents, mineral oils, stabilisers, flow enhancers, mould release agents, nucleating agents, clarifying agents and any combination thereof.

19. A particulate filler material for a flame retardant polymer composition,
20 the filler material comprising a mixture of a particulate clay and one or more further particulate flame retardant, wherein the particulate clay is a material according to any one of claims 1 to 9.

20. A particulate filler material according to claim 19, wherein the one or
25 more further particulate flame retardant comprises ATH.

21. A process for forming a polymer composition as defined in any one of
claims 11 to 18, comprising mixing a liquid or particulate solid polymer or one
or more precursor thereof with a material according to any one of claims 1 to 9
30 and any other desired components, and - if one or more precursor of the polymer component is present - subsequently curing the mixture.

22. A mixture of a liquid or particulate solid polymer or one or more precursor thereof and a particulate clay material according to any one of claims 1 to 9 and optionally any other components of a polymer composition as desired, for subsequent processing to form a polymer composition according to
5 any one of claims 11 to 18.

23. An article formed from a flame retardant polymer composition according to any one of claims 11 to 18.

10 24. A sheath, coating or housing for an electrical product, formed from a polymer composition as claimed in any one of claims 11 to 18.

ABSTRACT**PARTICULATE CLAY MATERIALS AND POLYMER**
COMPOSITIONS INCORPORATING THE SAME

5

A novel particulate clay material which is surface-modified with at least one organic compound comprising an organic portion such as an alkyl group and a basic portion such as an amine group has been found to be surprisingly useful as a filler material for a polymer composition, and especially a flame retardant

10

polymer composition. The composition preferably further contains alumina trihydrate (ATH) and/or another flame retardant.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.